

Technical Data Sheet

Perlite V-6

Description

Perlite is an amorphous volcanic glass that has relatively high water content. It's a mineral that occurs in nature and has the unusual property of greatly expand when it's heated.

When perlite reaches temperatures of 850-900 ° C, perlite softens (because it is a glass). Water trapped in the structure of the material is vaporized and escapes, and this causes the expansion of the material up to 20 times its original volume. The expanded material is a bright white, due to the reflectivity of the trapped bubbles.

Physical properties

- Color White
- Loose Density 35-60 kg/m³ (according PI 200-77)
- Compacted Density 45-80 kg/m³ (according PI 200-77)
- pH (in water) 7-10 (according PI 202-77)
- Sieve Analysis

| Mesh (µm) | % retained |
|-----------|------------|
| 1400 | < 3 % |
| 300 | 50-70 % |
| 150 | 15-25 % |
| 40 | 15-25 % |
| Dust | < 5 % |

- Free Moisture <0.5 % (according PI 118-77)
- Refractive Index 1.5
- Softening Temperature 1150-1250 °C
- Melting Temperature 1260-1350 °C
- Thermal Conductivity ≤ 0.04 W/mK a 20 °C (according ASTM 177)
- Heat Specific 0.84 kJ/kgK
- Combustibility Non combustible
- Asbestos Asbestos Free

Chemical Properties

| Chemical Composition | |
|-----------------------------------|---------|
| SiO ₂ | 70-80 % |
| Al ₂ O ₃ | 12-16 % |
| Na ₂ O | 2-5 % |
| K ₂ O | 2-5 % |
| CaO | 0-2 % |
| MgO | 0-1 % |
| Fe ₂ O ₃ | 0-1 % |
| H ₂ O (combined water) | <1 % |

Packaging

Perlite is packed in bags of 166 liters, with 26 bags for pallet. It also can be packed by big bags or tanker.